

# TEST 213 serial number: 1933

polyester/cotton fabric, 65/35, bleached

**generally:**

<b>according:</b>	Swissatest unsoiled test fabrics
<b>suitable:</b>	base material, load, and so on
<b>date of production:</b>	Oct 2019
<b>durability:</b>	Oct 2039
<b>storing conditions:</b>	must be well packed and kept dark

**specification of base material:**

<b>article 213</b>	polyester/cotton fabric, 65/35, bleached, without opt. brightener
<b>thread count in cm</b>	warp: 23.5 weft: 25.0
<b>yarn count in Nm</b>	warp: 34 weft: 34
<b>weight in g/m<sup>2</sup></b>	155.0
<b>width in cm</b>	147.0
<b>Y-value</b>	88.6
<b>Rem460nm</b>	86.7

**measuring conditions:**

instrument	DC800V (spectrophotometer)
illuminant / observer	D65 / 10°
measuring geometry	d/8°
wavelength range	420 to 750nm
filter	UV barrier at 420nm
measuring diameter	26 mm
gloss	excluded